TECHNOFORM

Material data sheet

Insulating strips of **PA 66 GF25 PCR 75**
closed-loop, dry impact resistant

Insulation solutions for windows, doors, and facades

TECHNOFORM

PA 66 GF25 PCR 75 closed-loop, dry impact resistant

Characteristic	Reference standard	Unit	Samples from extruded insulating strips	
			Dry (1)	Equilibrium moisture content (2)
Melting temperature	EN ISO 11357-3	°C	≥ 250 (3)	≥ 250 (3)
Density	EN ISO 1183-1 or -3	g/cm³	1.3 +/- 0.05	1.3 +/- 0.05
Annealing residue (glass fibre content)	EN ISO 1172	%	25 +/- 2.5	25 +/- 2.5
Tensile strength	EN ISO 527-2	N/mm²	≥ 60 (4)	≥ 40 (4)
Young's modulus	EN ISO 527-2	N/mm²	≥ 3100 (4)	≥ 1600 (4)
Elongation at break	EN ISO 527-2	%	≥ 4 (4)	≥8 (4)
Thermal conductivity	EN 12664	W/mK		0.3(5)
Reaction to fire	EN 13501-1	-		class E (6)

TBGroup-Do-TP1-47_V2_07.2026

The PA 66 GF25 used for production consists of up to 75% post consumer recycled materials from closed-loop sources. Material is suitable to be used as thermal barrier with mechanical functions according to EN 14024(7)

1) Sample water content less than 0.2 % by weight
2) Fast conditioning acc. to EN ISO 1110
3) Maximum temperature 300 °C
4) Specimen Type A22 - mean value with minimum sample size of 5 specimens at room temperature - tension measured in extrusion direction
5) The declared value is taken from ISO 10077-2 and can be used for thermal performance of frames according to the mentioned standard
6) Report 24-003934-PR02 ift Rosenheim GmbH
7) EN14024:2023 section 5.2 Report 24-003459-PR03 GAS-01-K21-11-en-01 ift Rosenheim GmbH

In case of specific questions we gladly offer you our individual support

Insulation solutions for windows, doors, and facades